

Označení fólie	CELKOVÁ SLUNEČNÍ ENERGIE								
	<i>propuštěná</i>	<i>odražená</i>	<i>absorbovaná</i>	<i>zamezená</i>	<i>propuštěné viditelné světlo</i>	<i>koefficient zatmavení</i>	<i>propustnost UV záření</i>	<i>snížení odlesku</i>	<i>zamezené IR záření (900 - 1000 nm)</i>
XPEL PRIME GL									
GL BLACK 5	44%	7%	49%	42%	5%	.66	<1%	95%	26%
GL BLACK 15	45%	6%	49%	41%	15%	.67	<1%	83%	26%
GL BLACK 20	47%	6%	47%	40%	20%	.69	<1%	78%	26%
GL BLACK 35	53%	6%	41%	36%	35%	.74	<1%	62%	25%
GL BLACK 50	60%	6%	34%	31%	50%	.80	<1%	45%	25%
XPEL PRIME HP									
HP BLACK 5	28%	8%	64%	59%	4%	.52	<1%	96%	43%
HP BLACK 15	30%	8%	62%	99%	13%	.54	<1%	86%	41%
HP BLACK 20	32%	8%	60%	53%	17%	.56	<1%	82%	40%
HP BLACK 35	43%	8%	54%	49%	34%	.65	<1%	63%	42%
HP BLACK 50	53%	8%	39%	36%	54%	.73	<1%	41%	42%
HP BLACK 70	70%	9%	21%	24%	70%	.87	<1%	23%	26%
HP BLACK 88	65%	8%	27%	27%	86%	.83	<1%	39%	58%
XPEL PRIME XR									
XR BLACK 5	11%	6%	83%	66%	5%	.39	<1%	95%	84%
XR BLACK 15	14%	6%	80%	65%	15%	.41	<1%	83%	85%

XR BLACK 20	16%	6%	78%	64%	19%	.40	<1%	81%	81%
XR BLACK 35	23%	6%	71%	60%	33%	.49	<1%	65%	84%
XR BLACK 50	35%	6%	59%	51%	55%	.56	<1%	34%	85%
XR BLACK 70	37%	7%	56%	48%	69%	.53	<1%	24%	88%